

AVAILABILITY

Seamless Pipe 1/2"-8"
 Weld Pipe 8"-12"
 Butt-Weld Fittings 1/2"-8"
 Bar 1"-8"

SPECIFICATIONS

ASTM A312, A403, A182
 ASME SA312, SA403, SA182

CHEMICAL COMPOSITION %

C	Cr	Mn	Mo	Ni	P	S	Si
Max		Max	Max		Max	Max	Max
.08	24.0-26.0	2.0	0.75	19.0-22.0	0.045	0.03	0.75

DESCRIPTION

310S has excellent resistance to oxidation under constant temperatures to 2000° F. Cyclic conditions reduce its oxidation resistance, and a maximum operating temperature of 1900° F is generally recommended if cycling is involved. Having a lower coefficient of expansion than most 300 stainless steels, 310S may be used in operations involving moderately severe thermal cycling, such as rapid air cooling. It is not usually recommended for liquid quenching. Although 310S has less resistance to absorption of carbon and nitrogen than the higher alloys such as 330 and 333, it is widely used in moderately carburizing atmospheres such as encountered in petro-chem plants. Because of its high chromium and medium nickel contents, 310S may be used in atmospheres containing moderate amounts of sulfur.

DESIGN FEATURES

- Austenitic stainless steel with excellent high temperature oxidation resistance.
- Good for continuous exposure to 2100° F, intermittent service to 1900° F.

- Better elevated temperature creep strength than the 18-8 grades.
- Good resistance to both carburizing and reducing environments.
- General corrosion resistance better than Type 304 and 309.
- May be susceptible to chloride stress corrosion cracking.
- Availability.
- Ease of fabrication.

TYPICAL APPLICATIONS

Heat exchanger and heat recuperator tubing
 Molten salt applications
 Sulfur bearing gas atmospheres

TENSILE REQUIREMENTS

Tensile Strength	Yield Strength
(KSI)	(KSI)
75	30

KSI can be converted to MPA (Megapascals) by multiplying by 6.895

James Duva Inc. stocks 310S with high Carbon to meet 310S/310H specifications.